

ADDENDUM No. 1

ITB No. 4377

Roof Replacement Project Fire Station 3

Due: April 7, 2015 at 2:00 P.M.

The following additions shall be made to the Invitation to Bid for Roof Replacement Project Fire Station 3, ITB No. 4377, on which proposals will be received on/or before April 7, 2015 by 2:00 P.M.

The information contained herein shall take precedence over the original documents and all previous addenda (if any), and is appended thereto. **This Addendum includes 2 pages.**

Bidder is to acknowledge receipt of this Addendum No. 1, including all attachments (if any) in its Bid by so indicating on P-1 of the Invitation to Bid Form. Bids submitted without acknowledgement of receipt of this addendum will be considered nonconforming.

I. ADDITIONS

Asbestos Containing Materials

Fire Station #3 existing roofing materials were tested for asbestos containing materials and none were detected as shown by the results provided on Page 2 herein.

Bidders are responsible for any conclusions that they may draw from the information contained in the Addendum. No other changes have been made. Acknowledge receipt of this Addendum with your Bid. If further assistance regarding this process is required, please contact Mark Berryman, Purchasing Manager by email at: mberryman@a2gov.org.

(This Space Intentionally Left Blank)



EMSL Analytical, Inc.

212 South Wagner Road, Ann Arbor, MI 48103
Phone/Fax: (734) 668-6810 / (734) 668-8532
http://www.EMSL.com annarborlab@emsl.com

EMSL Order: 081500535
CustomerID: NOVA63
CustomerPO:
ProjectID:


Attn: **Jeff Benya**
Nova Environmental, Inc
5300 Plymouth Rd
Ann Arbor, MI 48105

Phone: (734) 930-0995
Fax: (734) 930-2960
Received: 03/26/15 11:15 AM
Analysis Date: 3/26/2015
Collected:

Project: CI0168/*155/ City of Ann Arbor/ Fire Station #3/ Roof

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
CI0168/*155-001A 081500535-0001	Paper A	Black Fibrous Homogeneous	95% Cellulose	5% Non-fibrous (other)	None Detected
CI0168/*155-001B 081500535-0001A	Foam	Yellow Non-Fibrous Homogeneous		100% Non-fibrous (other)	None Detected
CI0168/*155-001C 081500535-0001B	Tectum	Beige Fibrous Homogeneous	70% Cellulose	30% Non-fibrous (other)	None Detected
CI0168/*155-001D 081500535-0001C	Paper B	Black Fibrous Homogeneous	95% Cellulose	5% Non-fibrous (other)	None Detected

Analyst(s) 
Rebecca Newman (4)


Ryan Shannon, Laboratory Manager
or other approved signatory

EMSL maintains liability limited to cost of analysis. This report relates only to the samples reported and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Samples received in good condition unless otherwise noted. Estimated accuracy, precision and uncertainty data available upon request. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Reporting limit is 1%
Samples analyzed by EMSL Analytical, Inc. Ann Arbor, MI NVLAP Lab Code 101048-4

Initial report from 03/26/2015 14:04:15